1,3-di-o-tolyguanidine		2	2	2	2	2
2-mercaptobenzothiazole		1	1	1	1	1
N-phenyl-N'-isopropyl-p-phenylenediamine			2	5		
N-(1,3-dimethylbutyl)-N'-phenyl-p-phenylenediamine					2	5
Item of Determination						
Mooney viscosity and scorch						
ML <sub>1+4</sub>	(pts)	29	29	26	29	26
$\mathrm{ML}_{\mathrm{min}}$	(pts)	29	29	26	29	26
t <sub>5</sub>	(min)	6.5	NG	NG	NG	NG
Rheometer curing properties						
ML	(N·m)	0.12	0.12	0.12	0.12	0.11
MH	(N·m)	0.52	0.12	0.11	0.12	0.11

(NG indicates that no date was obtained due to no crosslinking)

The Examiner is referred to the comments presented in applicants' Preliminary Amendment filed December 20, 2010.

Respectfully submitted,

Dated: <u>July 11, 2011</u> /Michael S. Gzybowski/

Michael S. Gzybowski, Reg. No. 32,816

Attorney for Applicant

**BRINKS HOFER GILSON & LIONE** 524 SOUTH MAIN STREET SUITE 200 ANN ARBOR, MI 48104 (734) 302-6046